

## CONE 6 GLAZE LOG SHEETS

[Black Gold](#) (small qty's only)

[Candy Red](#)

[Clear](#)

[Cream Breaking Red](#)

[Noxima Blue](#)

[Ohata Khaki](#)

[Opalescent Green](#)

[Purple Haze](#) (formerly "Plum")

[Sea Foam](#)

[Shino](#)

[Sky Black](#)

[Tenmoku](#) (Teadust)

[Turq – Red](#)

[White Liner](#)

[Woo Yellow](#)

## OHATA KHAKI Δ 6

Materials	%	Grams 8000 total	Date & Initials	Date & Initials	Date & Initials	Date & Initials	Date & Initials	Date & Initials
Gerstley Borate	31	2480						
Talc	14	1120						
Custer Feldspar	20	1600						
EPK (Kaolin)	5	400						
Flint (Silica)	30	2400						
ADD								
Red Iron Oxide	15	1200						

PURPLE HAZE Δ 6

Materials	%	Grams 8000 total	Date & Initials	Date & Initials	Date & Initials	Date & Initials	Date & Initials	Date & Initials
Gerstley Borate	8.4	672						
Nephylene Syenite	14	1120						
Custer Feldspar	27	2160						
Whiting (Calcium Carbonate)	12	960						
Lithium Carbonate	3.7	296						
Magnesium Carbonate	1.7	136						
Flint (Silica)	33	2640						
ADD								
Bentonite	2	160						
Cobalt Carbonate	0.6	48						
Chromium Oxide	0.17	13.6						
Tin Oxide	5	400						

## SEA FOAM Δ 6

Materials	%	Grams 8000 total	Date & Initials	Date & Initials	Date & Initials	Date & Initials	Date & Initials	Date & Initials
Lithium Carbonate	1	80						
Strontium Carbonate	20	1600						
Nephylene Syenite	60	4800						
Ball Clay (OM 4)	10	800						
Flint (Silica)	9	720						
ADD								
Titanium Dioxide	5	400						
Copper Carbonate	5	400						

## SKY BLACK Δ 6

Materials	%	Grams 8000 total	Date & Initials	Date & Initials	Date & Initials	Date & Initials	Date & Initials	Date & Initials
Gerstley Borate	10.7	856						
Whiting (Calcium Carbonate)	5.5	440						
Custer Feldspar	78.9	6312						
EPK (Kaolin)	4.9	392						
ADD								
Cobalt Oxide	2.1	168						
Copper Carbonate	4.1	328						
Manganese Dioxide	4.1	328						

TENMOKU GOLD (T-2) Δ 6

Materials	%	Grams 8000 total	Date & Initials	Date & Initials	Date & Initials	Date & Initials	Date & Initials	Date & Initials
Gerstley Borate	3.37	269.6						
Whiting (Calcium Carbonate)	6.98	558.4						
Cornwall Stone	67.41	5392.8						
Fling (Silica)	6.17	493.6						
Dolomite	7.86	628.8						
Lithium Carbonate	6.17	493.6						
ADD								
Red Iron Oxide	11.24	899.2						

TURQ-RED (RD-1) CΔ 6

Materials	%	Grams 8000 total	Date & Initials	Date & Initials	Date & Initials	Date & Initials	Date & Initials	Date & Initials
Gerstley Borate	10.67	853.6						
Dolomite	7.6	620.8						
Strontium Carbonate	4.7	333.6						
Whiting (Calcium Carbonate)	2.6	208						
Zinc Oxide	2.6	208						
Custer Feldspar	44.1	3528						
Frit 3110	9.7	776						
Flint (Silica)	16.3	1304						
ADD								
Tin Oxide	2.62	209.6						
Copper Carbonate	1.75	140						

WHITE LINER (W-2) Δ 6

Materials	%	Grams 8000 total	Date & Initials	Date & Initials	Date & Initials	Date & Initials	Date & Initials	Date & Initials
Nepheline Syenite	23	1840						
Frit 3124	23	1840						
Whiting (Calcium Carbonate)	14	1120						
EPK (Kaolin)	17	1360						
Flint (Silica)	23	1840						
ADD								
Zircopax	16	1280						



## WOO YELLOW Δ 6

Materials	%	Grams 8000 total	Date & Initials	Date & Initials	Date & Initials	Date & Initials	Date & Initials	Date & Initials
Dolomite	13	1040						
Strontium Carbonate	20	1600						
Nephylene Syenite	35.6	2848						
EPK (Kaolin)	7.6	608						
Flint (Silica)	7.6	608						
ADD								
Zircopax	6.2	496						
Bentonite	4.0	320						
Epson Salt	1	80						
Red Iron Oxide	3	240						

## BLACK GOLD Δ 6 – Small Quantities

Materials	%	Grams 2000 total	Date & Initials	Date & Initials	Date & Initials	Date & Initials	Date & Initials	Date & Initials
Redart Clay	49	980						
Manganese Dioxide	36.5	730						
OM4 Ball Clay	4	80						
Flint (Silica)	4	80						
Black Copper Oxide	4	80						
Cobalt Oxide	2.5	50						
ADD								
Bentonite	2	40						
Brushing Medium (CMC)	1.8	36						

CANDY RED Δ 6

Materials	%	Grams 8000 total	Date & Initials	Date & Initials	Date & Initials	Date & Initials	Date & Initials	Date & Initials
Gerstley Borate	21	1680						
Nephylene Syenite	16	1280						
EPK (Kaolin)	11	880						
Whiting	20	1600						
Flint (Silica)	32	2560						
ADD								
Tin Oxide	5	400						
Chromium Oxide	0.15	12						

CLEAR Δ 6

Materials	%	Grams 8000 total	Date & Initials	Date & Initials	Date & Initials	Date & Initials	Date & Initials	Date & Initials
Nephelene Syenite	30	2400						
Wollastonite	8	640						
Gerstley Borate	21	1680						
EPK (Kaolin)	10	800						
Flint*	31*	2480 + 400 2880						
ADD								
Strontium Carb	15	1200						

\*We increased the Flint by (5%) to reduce crazing

NOXIMA BLUE  $\Delta$  6

Materials	%	Grams 8000 total	Date & Initials	Date & Initials	Date & Initials	Date & Initials	Date & Initials	Date & Initials
Custer Feldspar	49.7	3976						
Wollastonite (Calcium Silicate)	23.9	1912						
EPK (Kaolin)	11.4	912						
Gerstley Borate	10.4	832						
Flint (Silica)	4.6	368						
ADD								
Cobalt Carbonate	2.8	224						

OPALESCENT GREEN Δ 6

Materials	%	Grams 8000 total	Date & Initials	Date & Initials	Date & Initials	Date & Initials	Date & Initials	Date & Initials
Custer Feldspar	41	3280						
Gerstley Borate	22	1760						
Whiting	9	720						
Strontium Carbonate	3	240						
Flint (Silica)	25	2000						
ADD								
Tin Oxide	3	240						
Copper Carbonate	5	400						
Rutile	5	400						

CREAM - RED Δ 6

Materials	%	Grams 8000 total	Date & Initials	Date & Initials	Date & Initials	Date & Initials	Date & Initials	Date & Initials
Custer Feldspar	41	3280						
Gerstley Borate	22	1760						
Whiting	9	720						
Strontium Carbonate	3	240						
Flint (Silica)	25	2000						
ADD								
Tin Oxide	12	960						
Rutile	12	960						

## SHINO Δ 6

Materials	%	Grams 8000 total	Date & Initials	Date & Initials	Date & Initials	Date & Initials	Date & Initials	Date & Initials
Nephylene Syenite	40	3200						
Soda Ash	12	960						
OM4 Ball Clay	15	1200						
Custer Feldspar	17	1360						
EPK	8	640						
Spodumene	9	720						
Red Art Clay	5	400						
Whiting	1	80						